



东莞明利钢材模具制品有限公司
Dongguan Minglee Steel Mould Products Co., Ltd.

M 明利集团成员 (Member of Ming Lee Group)

地址: 广东省东莞市大朗镇高英村高英路118号 邮编: 523771
电话: 0769-83316878 网址: www.minglee.com
传真: 0769-83317023, 83317036 电子邮箱: info@minglee.com

硬度对照表

Rockwell洛氏 HRC	Vickers维氏 HV	Brinell布氏 HB	Shore肖氏 HSD
68	959		97
67	923		95
66	889		92
65	856		91
64	825		92.0
63	795		89.8
62	766		87.6
61	739		85.8
60	713		83.6
59	688		81.8
58	664		80.4
57	642		78.0
56	620		76.2
55	599		74.4
54	579		72.6
53	561		71.0
52	543	514	69.4
51	525	501	68.0
50	509	488	66.4
49	493	474	64.8
48	478	461	63.4
47	463	449	62
46	449	436	60.4
45	436	424	59.2
44	423	413	57.8
43	411	401	56.6

Rockwell洛氏 HRC	Vickers维氏 HV	Brinell布氏 HB	Shore肖氏 HSD
42	399	391	55.4
41	388	380	54
40	377	370	53
39	367	360	51.6
38	357	350	50.6
37	347	341	49.6
36	338	332	48.4
35	329	323	47.2
34	320	314	46.2
33	312	306	45.2
32	304	298	44.2
31	296	291	43.2
30	289	283	42.2
29	281	276	41.2
28	274	269	40.4
27	268	263	39.6
26	261	257	38.6
25	255	251	37.8
24	249	245	37.0
23	243	240	36.4
22	237	234	35.4
21	231	229	34.6
20	226	225	34.0
19	221	220	33.2
18	216	216	32.6
17	211	211	31.8

注:以上表中之对换值只是近似值。